

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 June 2001 (07.06.2001)

PCT

(10) International Publication Number
WO 01/40384 A1

- (51) International Patent Classification⁷: C09C 1/48, C08K 3/04
- (21) International Application Number: PCT/US00/32863
- (22) International Filing Date: 1 December 2000 (01.12.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/168,542 2 December 1999 (02.12.1999) US
- (71) Applicant: CABOT CORPORATION [US/US]; Suite 1300, Two Seaport Lane, Boston, MA 02210-2019 (US).
- (72) Inventors: ATCHETEE, Michael, J.; 21 Leuvensebaan, B-3040 Ottenberg (BE). TOMME, Marcel, G.; Vuurkruisenlaan 4, B-9120 Beveren-Waas (BE). BHATT, Sandeep; 26 NewCastle Drive #9, Nashua, NH 03060 (US).
- (74) Agent: LANDO, Michelle, B.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:**
--- With international search report.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/40384 A1

(54) Title: CARBON BLACKS USEFUL IN WIRE AND CABLE COMPOUNDS

(57) Abstract: Novel carbon blacks are described wherein the carbon blacks have a nitrogen surface area of from about 65 to about 95 m²/g; an iodine number without additive of from about 64 to about 120 mg/g; a tinting strength of about 90 % or less; and a particle size of from about 22 nm to about 39 nm. Polymeric compositions containing at least one polymer and the carbon blacks of the present invention are further described as well as preferred polymeric compositions, such as wire and cable compounds containing the carbon blacks of the present invention in such uses as shielding compositions. Electrical conductors containing one or more layers which contain the carbon blacks of the present invention are further described as well as improved properties using the carbon blacks of the present invention.

CARBON BLACKS USEFUL IN WIRE AND CABLE COMPOUNDS

BACKGROUND OF THE INVENTION

The present invention relates to carbon blacks and further relates to their use in wire and cable compounds, such as shielding compositions. The present invention further relates to methods of incorporating these carbon blacks into wire and cable compounds and certain properties which can be achieved using the carbon blacks of the present invention.

Insulated cable is used extensively for transmission and distribution of electrical power. Two components of the power cable contain conductive carbon black- the strand shield and insulation shield. These carbon black filled semi-conductive materials are used to create an equipotential surface between the conductor and the insulation and to orientate the field in the insulation parallel to the conductor.

Carbon blacks are incorporated into the polymer composition through variety of mixing techniques. They are used extensively in the industry to render resistive polymers electrically conductive. The degree of electrical conductivity imparted by a specific carbon black is related to its physical and chemical properties. For carbon blacks with desired conductivity, it is generally desirable to utilize those carbon blacks that will provide as low viscosity as possible, and thus improve the processability of carbon black-polymer composition of the mixture. For cable applications, another important factor affecting extended cable life is smoothness at the shield interfaces. Any defect at the interfaces can increase the stress levels and may lead to premature cable failure. These defects are generally found to be caused by contaminants, degraded polymer gels, and/or poorly dispersed carbon black.

The power cables designed for medium to high voltage applications have a copper or aluminum core conductor, a layer of semi-conductive shielding, a layer of insulation, and a layer of semi-conductive insulation shielding. The insulation layer is predominantly either crosslinked polyethylene or crosslinked ethylene propylene rubber (EPR). During the installation of the cable it is often necessary to make splices and terminal connections, this requires the clean delamination of the insulation shield layer from the insulation layer. Therefore, a strippable semi-conductive insulation shielding which can be easily stripped from the insulation layer will be desirable. However, a minimum strip force is required to maintain the mechanical integrity between the insulation layer and the semi-conductive insulation; if the force is too low then loss of adhesion may result in water diffusing along the interface causing electrical breakdown.

Accordingly, it will be advantageous to produce novel carbon black that can impart at the same time higher compound conductivity at a comparatively lower viscosity and high level of smoothness and a low adhesion in strippable formulations. These and other advantages are achieved

-2-

by the carbon black and polymer compositions of the present invention.

SUMMARY OF THE INVENTION

5 A feature of the present invention is to provide novel carbon blacks which preferably provide one or more improved properties to the wire and/or cable compounds.

The present invention also relates to polymeric compositions, such as wire and cable compounds, containing the carbon blacks of the present invention.

Another feature of the present invention is to provide carbon blacks, which when incorporated into wire and cable compounds, provide a low viscosity.

10 In addition, a feature of the present invention is to provide carbon blacks, which when incorporated into wire and cable compounds, lead to an acceptable and higher conductivity ranges.

A further feature of the present invention is to provide carbon blacks which when incorporated into wire and cable compounds promote a very high smoothness of the formed compound.

15 An additional feature of the present invention is to provide carbon blacks, which when incorporated into wire and cable compounds, promote a very good stripability of the layer containing the carbon black.

Also, a feature of the present invention is to provide carbon blacks, which when incorporated into wire and cable compounds, provides a combination of all of the above-described properties.

20 Additional features and advantages of the present invention will be set forth in part in the description which follows, and in part will be apparent from the description, or may be learned by practice of the present invention. The objectives and other advantages of the present invention will be realized and obtained by means of the elements and combinations particularly pointed out in the written description and appended claims.

25 To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described herein, the present invention relates to a conductive carbon black having a nitrogen surface area of from 65 to 95 m²/g; an Iodine number without additive of from 64 to 120 mg/g; a tinting strength of about 90% or less; and a ASTM particle size of from 22 nm to 39 nm.

30 The present invention further relates to polymer compositions, such as cable and wire compounds, containing the above-described carbon black.

In addition, the present invention relates to a polymer composition containing the above-described carbon black, an ethylene containing polymer, and a crosslinking agent. This polymer composition can further contain an acrylonitrile butadiene type polymer and/or other conventional

-3-

additives.

Furthermore, the above-described carbon black can be further treated with a variety of one or more treating agents such as a polymer comprising an acrylonitrile and at least one other monomer; ethoxylated esters or polyethers; compounds containing at least one long chain alkenyl or alkyl group and at least one amine group; alkylene type compounds such as polyethylene glycol, and the like.

In addition, the present invention relates to methods to lower viscosity, improve conductivity, improve smoothness, and/or improve stripability of the wire and cable compound using the carbon blacks of the present invention.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are intended to provide a further explanation of the present invention, as claimed.

DETAILED DESCRIPTION OF THE PRESENT INVENTION

The present invention relates to novel carbon blacks and their use in polymeric compositions such as wire and cable compounds. Preferably, the use of the carbon blacks in the wire and cable compounds leads to improved properties such as one or more of the following: a lowered viscosity of the wire and cable compounds; an improved conductivity range; an improved smoothness of the formed wire and/or cable compound; and/or an improved stripability of the formed wire and/or cable compound.

The carbon black of the present invention preferably has a nitrogen surface area of from about 65 to about 95 m²/g as measured by ASTM D4820. The carbon black further has an Iodine number without additive of from about 64 to 120 mg/g as measured by ASTM D1510. The carbon black further has a tinting strength of 90% or less as measured by ASTM D3265; and a ASTM particle size of from about 22 nm to about 39 nm as measured by ASTM D3849-89.

The carbon black of the present invention can further have one or more of the following additional characteristics which are preferred: a DBPA of from about 119 to about 128 cc/100g as measured by ASTM D2414 and preferably a DBPA of from about 120 to about 124 cc/100g and even more preferably 123 cc/100g.

Preferably, the carbon blacks of the present invention have a nitrogen surface area of from about 65 to about 75 m²/g, more preferably 66 m²/g to 75 m²/g, and even more preferably 68 m²/g to 72 m²/g, and most preferably 70 m²/g; an Iodine number without additive of from 78 to 85 mg/g and more preferably 80 to 85 mg/g, and even more preferably 83 mg/g; a tinting strength of from about 75% to about 90% and more preferably about 81%; an ASTM particle size of from about 30 to about 38 nm, and even more preferably about 34 nm. Other ranges of characteristics include, but are not limited to,

-4-

a nitrogen surface area of from 65 m²/g to 72 m²/g, such as 68 m²/g; a DBPA range of from 120 to 127 cc/100g, such as 123 cc/100g; an Iodine number of from 80 to 90 mg/g; a tinting strength of from 75 to 85%, such as 80%. The present invention can use carbon blacks having these characteristics or use carbon blacks outside of these characteristics but still within the broader defined characteristics as set forth earlier. Also, the carbon blacks can be used as strippable conductive wire or cable compounds as described below or can be used in other types of articles as described throughout the present application.

The carbon blacks of the present invention can be made using the furnace as described in U.S. Patent No. 5,877,250, which is incorporated herein in its entirety by reference. Preferably, in following the process described in U.S. Patent No. 5,877,250, the primary combustion level is less than 600%, preferably less than 400%, and more preferably from about 180 to about 320%. Preferably, the overall combustion level of the process is about 30% or less, preferably from about 20% to about 30%, more preferably from about 24% to about 27%. It is also preferred that the residence time for the carbon black forming reactions in the process for producing the carbon blacks of the present invention is .55 seconds to 9.99 seconds, more preferably from about 1.3 seconds to about 6.58 seconds. With respect to the ratio of air to natural gas, this ratio is at least 30:1, preferably is less than 60:1, and more preferably is less than 40:1 and even more preferably is from about 18:1 to about 32:1. In referring to the furnace described in U.S. Patent No. 5,877,250, the feedstock may be introduced either through a probe 15 or radially inward through a plurality of opening positioned in the wall of zone 12 at point 32 or a combination of the two. The feedstock introduced through the probe 15 can be altered by changing the number of injection openings. The angle of the openings can vary from a direction axially with the reaction centerline or radially up to and including perpendicularly to the reactor centerline. In addition, the position of the probe may be altered along the centerline of the reactor from position 32.

Finally, the feedstock sulfur amount is preferably less than 1000 ppms, though higher amounts can be used. Generally, with the above-described preferred parameters in following the process described in U.S. Patent No. 5,877,250, carbon blacks having the above-described properties of the present invention can be made. Further alterations to the process can be made by those skilled in the art in view of the present description once the desired parameters, as described above, are used as objectives in running the furnace to form the carbon blacks.

Preferably, the carbon blacks which are formed are furnace carbon blacks, however other carbon blacks can be made, such as channel blacks or acetylene blacks. The carbon blacks of the present invention can be in fluffy form or pelletized form and the pellets can be formed using conventional techniques which are known to those skilled in the art.

The carbon blacks of the present invention can be further treated with a variety of treating agents, such as binders and/or surfactants. The treating agents described in U.S. Patent Nos. 5,725,650;

-5-

5,200,164; 5,872,177; 5,871,706; and 5,747,559, all incorporated herein in their entirety by reference, can be used in treating the carbon blacks of the present invention. Other preferred treating agents, including surfactants and/or binders, can be used and include, but are not limited to, polyethylene glycol; alkylene oxides such as propylene oxides and/or ethylene oxides, sodium lignosulfate; acetates such as ethyl-vinyl acetates; sorbitan monooleate and ethylene oxide; ethylene/styrene/butylacrylates/methyl methacrylate binders; copolymers of butadiene and acrylonitrile; and the like. Such binders are commercially available from such manufactures as Union Carbide, ICI, Union Pacific, Wacker/Air Products, Interpolymer Corporation, and B.F. Goodrich. These binders are preferably sold under the trade names: Vinnapas LL462, Vinnapas LL870, Vinnapas EAF650, Tween 80, Syntran 1930, Hycar 1561, Hycar 1562, Hycar 1571, Hycar 1572, PEG 1000, PEG 3350, PEG 8000, PEG 20000, PEG 35000, Synperonic PE/F38, Synperonic PE/F108, Synperonic PE/F127, and Lignosite-458.

Generally the amount of treating agent used with the carbon blacks of the present invention can be the amounts recited in the above-described patents, for instance in an amount of from about 0.1% to about 50% by weight of the treated carbon black, though other amounts can be used depending upon the type of properties desired and the particular treating agent(s) being used.

With respect to the polymer compositions, the carbon blacks of the present invention can be incorporated into any polymeric composition containing one or more polymers and optionally other conventional additives. The carbon blacks of the present invention can be used in elastomeric and rubber compositions. Preferably, the composition is an ethylene containing polymer or elastomer, such as, but not limited to, polyethylene or an ethylene copolymers, ethylene-propylene rubber, ethylene-vinyl acetate (EVA), and/or ethylene ethyl acrylate (EEA). Therefore, articles of manufacture containing the carbon blacks of the present invention can be made. A preferred article of manufacture is an extruded article, such as a profile, tube, tape, or film. Another preferred article is a strippable conductive wire or cable coating compound. Also preferred as an article of manufacture of the present invention is a medium or high voltage cable comprising:

- A metal conductor core;
- A semi-conductive shield;
- An insulation layer; and
- An outer semi-conductive layer.

The carbon blacks of the present invention can be present in a shielding composition and/or outer semi-conductive layer. These compositions are known as strand shielding compositions and insulation compositions.

The novel carbon blacks of the present invention can be incorporated into conventional polymer compositions using conventional amounts. For instance, the carbon blacks of the present invention can

-6-

be incorporated into shielding compositions in conventional amounts such as from about 1% to about 50% by weight of the shielding composition, and more preferably from about 15% to about 45 % based on the weight of the shielding composition, and most preferably from about 30% to about 40% by weight of the shielding composition.

5 Preferably, the shielding compositions of the present invention contain an ethylene containing polymer or polyethylene such as an ethylene-vinyl acetate copolymer and a crosslinking agent such as an organic peroxide crosslinking agent. The shielding compositions of the present invention can further contain other polymers such as an acrylonitrile butadiene polymer (e.g., an acrylonitrile butadiene copolymer). If the carbon black has a treating agent on it, such as in the form of an acrylonitrile
10 butadiene copolymer, then the amount of acrylonitrile butadiene polymer or other polymer(s) that may be present can be reduced or eliminated in the shielding composition

Preferably, the ethylene containing polymer is an ethylene-vinyl acetate copolymer or EEA which is preferably present in an amount of from 20 to about 50% by weight based on the weight of the shielding composition and more preferably, from about 25 to about 45 weight %.

15 The carbon blacks of the present invention can be substituted for the conventional carbon blacks described in European Patent Application No. 0 420 271; U.S. Patent No. 5,747,559; 5,871,706; 5,872,177; and 5,725,650, all of which are incorporated herein in their entirety by reference.

Typically, the semi-conductive compositions may be made by combining one or more polymers with an amount of carbon blacks sufficient to render the composition semi-conductive. Similarly, the
20 insulating materials may be formed by incorporating minor amounts of carbon black, for example, as a colorant, into a polymer composition. Insulating material may be formed by combining a polymer and an amount of carbon black much less than that sufficient to impart semi-conductive properties to the material. For example, the polymeric compositions of the present invention may be made by combining a polymer, such as a polyolefin, with an amount of carbon black sufficient to render the composition
25 semi-conductive.

The compositions of the present invention may also include suitable additives for their known purposes and known and effective amounts. For example, the compositions of the present invention may also include such additives as cross-linking agents, vulcanizing agents, stabilizers, pigments, dyes, colorants, metal deactivators, oil extenders, lubricants, inorganic fillers, and the like.

30 The polymeric compositions of the present invention can be made using conventional techniques such as mixing the various components together using commercially available mixers. The compositions can then be formed into the desired thickness and length and width using conventional techniques known to those skilled in the art, such as described in EP 0 420 271; U.S. Patent Nos. 4,412,938; 4,288,023; and 4,150,193 all incorporated herein in their entirety by reference. In more

-7-

detail, the polymer compositions of the present invention may be manufactured using conventional machinery and methods to produce the desired final polymer product. The composition may be prepared by batch or continuous mixing processes such as those well known in the art. For example, equipment such as Banbury mixers, Buss co-kneaders, and twin screw extruders may be used to mix the ingredients of the formulations. For instance, the components of the polymer compositions of the present invention may be mixed and formed into pellets for future use in manufacturing such materials as insulated electrical conductors.

The polymer compositions of the present invention may be incorporated into any product where the properties of the polymer compositions are suitable. For example, the polymer compositions are particularly useful for making insulated electrical conductors, such as electrical wires and power cables. Depending on the conductivity of the polymer compositions, the polymer composition may be used, for example, as a semi-conductive material or as an insulating material in such wires and cables. More preferably, a semi-conductive shield of the polymer composition may be formed directly over the inner electrical conductor as a conductor shield, or over an insulating material as a bonded or strippable insulation shield, or as an outer jacketing material. The carbon blacks in the selected polymer compositions may also be used in strand filling applications in either conductive or nonconductive formulations.

Typically, the components of an electric cable are a conductive core (such as a multiplicity of conductive wires) surrounded by several protective layers. Additionally, the conductive core may contain a strand filler with conductive wires, such as a water blocking compound. The protective layers include a jacket layer, an insulating layer, and a semi-conductive shield. In a cable, typically conductive wires will be surrounded by a semi-conductor shield which in turn is surrounded by an insulation layer which in turn is surrounded by a semi-conductor shield and then a metallic tape shield, and finally, the jacket layer.

The carbon blacks of the present invention preferably provide a balance of beneficial properties to polymeric compositions, such as wire and cable compounds. Preferably, the carbon blacks of the present invention, when present in wire and cable compounds provide good viscosity, high smoothness, acceptable conductivity, and good stripability. It is unusual for one type of carbon black to provide two of these properties and yet the present invention has the ability to provide at least two, three, or most preferably, all four properties.

As stated earlier, the carbon blacks, when incorporated into wire and cable compounds, have the ability to provide or promote a lower viscosity which improves the ability to disperse the carbon black throughout the polymeric composition. The carbon blacks of the present invention also preferably improve the conductivity range of the shielding composition such that volume resistivity is about 120

5 Ω .cm or less, per ISO 3915 at 35% by weight loading in EEA, and more preferably is about 50 Ω .cm or less, and even more preferably about 30 Ω .cm or less. In addition, the carbon blacks of the present invention promote a high smoothness of the formed shielding composition such that the number of defects per dm^2 is about 7000 or less, more preferably about 3000 or less at a 35% by weight loading in EEA. The carbon blacks of the present invention when incorporated into wire and cable compounds promote a good stripability of the shielding layer, such that strip force is about 20 lb/0.5 in. or less, and more preferably about 15 lb/0.5 in. or less at 36 weight % loading of carbon black in EVA. With respect to viscosity, the viscosity is preferably about 2600 cps or less and more preferably is about 2000 cps or less at a 35 weight % loading of carbon black in EEA at 190°C at a shear rate of 100/s. All of these
10 above properties are shown for exemplary purposes only and other ranges are obtainable.

The present invention will be further clarified by the following examples, which are intended to be purely exemplary of the present invention.

EXAMPLES

15 Mixing of the compounds was carried out on the PR46 Buss Kneader. The polymer used for the evaluation of conductivity, viscosity, and smoothness was an EEA copolymer routinely used in the industry for the production of strand shield compounds. Before mixing, all carbon blacks were gently homogenized in 120 liter drums (by rolling the drums on the floor). The carbon black was fed by the two entries of the mixer, the feeding ratio between first and second entry kept constant at 0.9. The temperature of the extruder was kept around 180°C and 200°C on the die. The extruder was operated
20 at the speed of 16 rpm. For evaluation of the stripability, a compound based on a 40% EVA copolymer was used. These compounds were made on a Banbury internal mixer.

The four point measurement method described in ISO 3915 was chosen to measure volume resistivity since it is a widely accepted international standard describing the determination of volume resistivity in conductive plastic materials. Its major advantage lies in the fact that it totally prevents any
25 influence of the contact resistance between the sample and the measurement circuit on the reading. The material is compression molded at 180°C in one step in a Fontijne press equipped with a microprocessor. The dimensions of the plaque are 200 X 200 X 3 mm. The molding cycle takes 17:00 minutes. The material is first heated at 180°C during 10 minutes then cooled down to 50°C. Six specimens of 10 mm x 50 mm x 3 mm were prepared and tested as per the procedure.

30 Viscosity measurements were performed on a Göttfert 2002 rheometer, equipped with a 30 x 1 mm capillary die at 190°C at different shear rates. This was done by extruding the product through a capillary die by means of a speed controlled piston and recording the melt pressure. The viscosity is the ratio between the shear stress and the shear rate. These dimensions are calculated from the piston speed and the melt pressure. Table 3 sets forth the viscosity results in pascals obtained at apparent shear rates

of 100 and 1000 s⁻¹ at given temperatures.

The tape surface smoothness was measured by means of image analysis. The tapes were extruded, using a 19mm, 20 L/D Brabender extruder, with three heating zones (barrel and die). The temperature settings were 130, 140 and 150°C, the extrusion speed was 15 rpm. A 50 x 0.5 mm flat die was used and the tape was stretched to obtain a thickness of 0.25 mm. A video camera, positioned above the slowly moving tape, was used to collect images that were read into an image analysis system. After enhancement and processing of the images, the system identified, counted and sized the surface defects. The results in these size classes are presented in Table 4 as the number of defects per dm².

The strip force on the blacks were measured using the standard strip test procedure used in Cabot Corporation. Insulation shield compound was prepared by mixing blacks with EVA in Kobelco mixer, while HDPE was used as insulation layer. Individual plaques of both the insulation layer and insulation shield materials were prepared by compression molding the pelleted materials at 250°F (121°C); this temperature allowed smooth plaques to be formed without activation of the organic peroxide. The two layers were then laminated at 250°F (121°C) for 5 minutes to allow prewetting and then cured at 356°F (180°C) for 15 minutes. The dimensions of the final plaque are 4" x 12" (100 mm x 300 mm). The insulation layer has a thickness of 0.039" (1 mm) and the insulation shield has a thickness of 0.079" (2 mm). Six strips of 0.5" x 12" (12.5 mm x 300 mm) were cut in the semi-conductive layer, the insulation layer is not cut thus maintaining a more rigid strip substrate. The strips were debonded from the plaque by using an imass peel tester. The force in pounds necessary to peel or strip the semi-conductive EVA layer from the polyethylene insulation at an angle of 180° was recorded.

The semi-conductive compositions containing the following carbon blacks were prepared. The amount of all the ingredients based on weight percent is given in Table 1B.

Table 1A

Property	Test Procedure		Black A	Black B	Black C
Iodine number*	ASTM D1510	(mg/g)	44	170	83
Nitrogen surface area	ASTM D4820	(m ² /g)	40	147	70
DBPA	ASTM D2414	(cc/100g)	123	117	123
Tint	ASTM D3265	%	56	92	81
ASTM particle size	ASTM D3849-89	(nm)	42	17	34

*Measured on blacks without any additive

Black A: Elftex 280 - N550 type

Black B: Vulcan® PA 90 - P type

Black C: Present Invention

Table 1B

Composition		Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Black Type		A	A	B	B	C	C
Carbon black	wt %	35	38	35	38	35	38
EEA	wt %	64.5	61.5	64.5	61.5	64.5	61.5
Stabilizer	wt%	0.5	0.5	0.5	0.5	0.5	0.5

As shown in Table 2, the lower volume resistivity of the Black C as compared to Black A shows an advantage for use in cable compounds. If manufacturers have a targeted volume resistivity as the criteria, lower loading of the new black can provide them with the desired conductivity compared to the widely used blacks (like Black A) for this application. As shown in Table 2, even at 35% (example 5) loading Black C has better conductivity as compared to Black A at 38% (example 2) loading. Black C has lower or equivalent conductivity as Black B as shown in the table below.

Table 2

Composition		Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Black Type		A	A	B	B	C	C
Carbon black	wt %	35	38	35	38	35	38
Volume Resistivity*	$\Omega \cdot \text{cm}$	32.7	14.7	9.3	6.1	9.9	3.7

*As per ISO 3915

The lower viscosity improves the processability of the mixtures of the carbon black and molten polymer, and therefore is a particularly important and useful property of such compositions. As shown in Table 3, at equivalent conductivity the novel Black C can be used at a lower loading as compared to widely used blacks of lower surface area like Black A. The lower loading of carbon black can lead to further reductions in the compound viscosity. Therefore, manufacturers of the compounds can increase the throughput on their existing manufacturing lines and thus get substantial reduction in the manufacturing costs of the materials. Black C has slightly higher viscosity as compared to Black B.

Table 3

Composition		Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Black Type		A	A	B	B	C	C
Carbon black	wt %	35	38	35	38	35	38
Viscosity of Compound at 190C in EEA at the Apparent Shear rate of							
	100/s	1013	1235	1102	1333	1268	1609
	1000/s	218	248	233	270	282	336

Table 4 shows the data on tape surface smoothness using image analysis. The number of defects have been classified into two categories, i.e., 50-200 μ m and greater than 200 μ m defects. The novel Black C clearly showed the better surface smoothness as compared to the more conventional Black A and Black B used currently in the cable applications.

Table 4

Composition		Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Black Type		A	A	B	B	C	C
Carbon black	wt %	35	38	35	38	35	38
Defects/ dm ²	50-200 μ m	5653	3077	1039	472	273	10
	> 200 μ m	2	1	12	11	1	0

Table 5 shows the strip force measured on the laminates as per the standard procedure described above. The results show that compound made with Black C has slightly higher strip force compared to Black A at equal loading, but has significantly lower strip force compared to Black B. This lower strip force imparted to compounds made with Black C, makes it a very desirable carbon black for insulation shield compounds.

Table 5

		Example 1	Example 2	Example 3	Example 4
Black Type		A	B	C	C
Carbon black	wt %	38	36	38	36
EVA*	wt%	60.5	62.5	60.5	62.5
Dicumyl Peroxide	wt%	1	1	1	1
Stabilizer	wt%	0.5	0.5	0.5	0.5
Peel Force	lb/0.5 in	7.2	16.2	8.6	10.1

*Polyethylene vinyl acetate

Other embodiments of the present invention will be apparent to those skilled in the art from consideration of the specification and practice of the present invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the present invention being indicated by the following claims and equivalents thereof.

WHAT IS CLAIMED IS:

1. A conductive carbon black having a nitrogen surface area of from about 65 to about 95 m²/g; an Iodine number without additive of from 64 to 120 mg/g; a tinting strength of about 90% or less; and
5 an ASTM particle size of from about 22 to about 39 nm.
2. The carbon black of claim 1, wherein said carbon black has a DBPA of from about 119 to about 128 cc/100g.
3. The carbon black of claim 1, wherein said nitrogen surface area is from about 65 to about 75 m²/g.
- 10 4. The carbon black of claim 1, wherein said Iodine number without additive is from about 78 to about 85 mg/g.
5. The carbon black of claim 1, wherein said tinting strength is from about 75% to about 90%.
6. The carbon black of claim 1, wherein said particle size is from about 30 to about
15 38 nm.
7. The carbon black of claim 1, wherein said nitrogen surface area is from about 65 to about 75 m²/g, said Iodine number without additive is from about 78 to about 85 mg/g, said tinting strength is from about 75% to about 90%, and said particle size is from about 30 to about 38 nm.
- 20 8. The carbon black of claim 1, wherein said carbon black has a nitrogen surface area of about 70 m²/g; an Iodine number without additive of about 83 mg/g; a tinting strength of about 81%; and an ASTM particle size of about 34 nm.
9. A polymeric composition comprising at least one polymer and the carbon black of claim 1.
- 25 10. A polymer composition comprising an ethylene containing polymer, the carbon black of claim 1, at least one crosslinking agent.
11. The polymer composition of claim 10, wherein the ethylene containing polymer comprises an ethylene vinyl acetate polymer, an ethylene propylene rubber, an ethylene propylenediene monomer, or mixtures thereof.
- 30 12. The polymer composition of claim 10, further comprising at least one acrylonitrile butadiene or derivative thereof.
13. A semi-conductive insulation shielding composition comprising the carbon black of claim 1, at least one ethylene-vinyl acetate copolymer; at least one acrylonitrile butadiene copolymer; and at least one crosslinking agent.

-13-

14. An article of manufacture comprising the polymer composition of claim 10.

15. An electrical conductor comprising a semi-conductive layer, wherein said semi-conductive layer comprises the polymer composition of claim 10.

16. The carbon black of claim 1, wherein said carbon black is a treated carbon black.

5 17. The polymeric composition of claim 9, wherein said polymer comprises at least one rubber or elastomer.

18. The carbon black of claim 1, wherein said nitrogen surface area is from 68 m²/g to 72 m²/g.

10 19. A polymeric composition comprising at least one polymer and the carbon black of claim 18.

20. The carbon black of claim 1, wherein said nitrogen surface area is from 66 m²/g to about 95 m²/g.

21. A polymeric composition comprising at least one polymer and the carbon black of claim 20.

INTERNATIONAL SEARCH REPORT

In .ational Application No

PCT/US 00/32863

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09C1/48 C08K3/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09C C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No
X	US 5 877 250 A (SANT RAVINDRA) 2 March 1999 (1999-03-02) cited in the application the whole document ---	1-21
A	GB 1 564 080 A (CABOT CORP) 2 April 1980 (1980-04-02) ---	
A	GB 1 501 967 A (CONTINENTAL CARBON CO) 22 February 1978 (1978-02-22) -----	

☐ Further documents are listed in the continuation of box C

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

9 March 2001

Date of mailing of the international search report

19. 03. 2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

LIBBERECHT, E

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 00/32863

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.:
because they relate to parts of the international Application that do not comply with the prescribed requirements to such an extent that no meaningful international Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Present claims 1-21 relate to a product defined by the parameters as defined in claims 1-8

by reference to the following parameter(s):

p1:nitrogen surface area

p2:iodine number

p3:tinting strenght

p4:astm particle size

p5: dbpa

The use of these parameters in the present context is considered to lead to a lack of clarity within the meaning of Article 6 PCT. It is impossible to compare the parameters the applicant has chosen to employ with what is set out in the prior art. The lack of clarity is such as to render a meaningful complete search impossible.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

Ir. International Application No

PCT/US 00/32863

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5877250 A	02-03-1999	AU 709161 B	26-08-1999
		AU 1830197 A	22-08-1997
		BR 9704620 A	09-06-1998
		CA 2216792 A	07-08-1997
		CN 1183114 A	27-05-1998
		CZ 9703068 A	18-02-1998
		EP 0817814 A	14-01-1998
		HU 9901666 A	30-08-1999
		JP 11503486 T	26-03-1999
		NO 974461 A	28-11-1997
		PL 322554 A	02-02-1998
		WO 9728222 A	07-08-1997
		US 5877251 A	02-03-1999
GB 1564080 A	02-04-1980	AR 217833 A	30-04-1980
		AU 506109 B	13-12-1979
		AU 2564077 A	07-12-1978
		BR 7703817 A	18-04-1978
		CA 1081433 A	15-07-1980
		CS 249103 B	12-03-1987
		DD 156601 A	08-09-1982
		DE 2726183 A	29-12-1977
		DK 264477 A,B,	17-12-1977
		ES 459807 A	01-04-1978
		FR 2354894 A	13-01-1978
		HK 92784 A	30-11-1984
		IE 45221 B	14-07-1982
		IL 52090 A	29-02-1980
		IT 1083430 B	21-05-1985
		JP 1292582 C	16-12-1985
		JP 52153892 A	21-12-1977
		JP 55027111 B	18-07-1980
		LU 77532 A	25-10-1977
		MX 144976 A	09-12-1981
		NL 7706649 A,B	20-12-1977
		NZ 184214 A	28-03-1979
		PH 13249 A	20-02-1980
		PL 198879 A	24-04-1978
		PT 66653 A,B	01-07-1977
		SE 426955 B	21-02-1983
		SE 7706922 A	17-12-1977
		TR 20282 A	19-12-1980
		US 4105750 A	08-08-1978
		YU 149977 A	30-06-1982
		ZA 7703029 A	26-04-1978
		BE 855711 A	03-10-1977
		RO 76287 A	04-11-1981
GB 1501967 A	22-02-1978	AU 8267775 A	06-01-1977
		ES 439606 A	16-06-1977
		IN 143558 A	24-12-1977
		NL 7508808 A	27-01-1976